

# Effect of Copper Content on Wear Properties of Aluminium Alloy

B. Chandra Mouli\*, D. Naresh, K.S.J. Prakash, A. Bala Krishna

Department of Mechanical Engineering, RISE Krishna Sai Prakasam Group of Institutions, Ongole, Andhra Pradesh, India

\*Corresponding author: E-Mail: badiganti1@gmail.com

## ABSTRACT

Aluminium alloys are extensively used in aircraft, automobile and other engineering structures. The reason for this large application is due to a wide range of excellent properties including low density, corrosion resistance and high strength to weight ratio excluding its strength. In this paper Al-Cu binary alloy is considered in different weight proportions with aluminium as main component and varying copper content from 2-6% in weight. Wear test were carried out using a pin on disc apparatus and found that there is more wear in Al-6Cu composition by 38%.

**KEY WORDS:** Sand casting, Wear, Aluminium alloy.

## 1. INTRODUCTION

Aluminium alloys are extensively used in aerospace, automobile, medical industries due to their light weight and high weight to strength ratio. However, aluminium by itself exhibits poor tribological properties. Hence, tribological behaviour of Aluminium is gaining more attention by Venkataraman and Sundararajan (2010). Jiang and Tan (1996), have studied the influence of alumina fibre reinforced in Al-Si alloy composites in dry sliding wear condition behaviour. It was found that reinforced alloy has underwent to severe wear at a high load as compared to the unreinforced alloy. Perrin and Rainforth (1995), studied the size of the subgrains below the worn surface of an Al-Cu alloy and found a minimum value at a certain depth below the worn surface due to saturation of flow stress but, reinforcing Al-Cu alloy with alumina fibres a uniform size of the subgrains can be attained below the worn surface as the fibres could distribute the load uniformly.

With a view to remove the gaps in the above literature at least partially in our current level of understanding, wear experiments with different test loads (10 N, 30 N) were conducted with Al-2Cu, Al-3Cu, Al-4Cu, Al-5Cu, Al-6Cu Aluminium alloy as the test material (in the form of pins) sliding against hardened steel discs. The results of the above experiments are discussed in this paper.

## 2. EXPERIMENTATION

**Materials:** The materials used in the present study were as follows: (a) Al- 2% Cu alloy (b) Al- 3% Cu alloy (c) Al- 4% Cu alloy (d) Al- 5% Cu alloy and (e) Al- 6% Cu alloy. The various Al-Cu composition alloys were fabricated using Sand Casting route.

**Sliding Wear Tests:** The wear tests were carried out using a Pin-on-Disc tribometer machine as shown in Fig.1. It consisted of a steel disc that was carried by a mandrel driven by a motor. The test specimens consisted of two cylindrical pins that were mounted on a hydraulic loading mechanism consisting of dead weights, spindle and hydraulic cylinder. The specimen to be tested is fixed to the collect and the collect along with the specimen is positioned at a 80mm track diameter. This track diameter is to be changed after each test i.e., a fresh track is to be selected for each specimen. During the experiment specimen remains fixed and disc rotates. Load is applied through a dead weight loading system to press the pin against the disc and frictional force raised at the contact can be read out from the controller. For each composition of Aluminium Copper alloy a 5 sets of specimens were tested and average was taken. Each set of test is carried out for a period of one hour. After each one hour run the test pieces were removed from the machine and weighted accurately to determine the loss in weight. The test was repeated for 10N and 30N load at 800rpm.




Figure.1. Pin on Disc Tribometer

**Table.1. Specifications of equipment**





|                                   |                              |
|-----------------------------------|------------------------------|
| Conforms to the specifications of | ASTM G99                     |
| Sliding Speed Range               | 0.26-10 m/sec                |
| Disc Rotation Speed               | 100-2000 rpm                 |
| Maximum Normal Load               | 200 N                        |
| Frictional Force                  | 0-200 N                      |
| Wear Measurement Range            | 4 mm                         |
| Pin Size                          | 3-12 mm diagonal/diameter    |
| Disc Size                         | 160 mm diameter x 8 mm thick |
| Wear Track Diameter               | 10-140                       |

### 3. RESULTS AND DISCUSSION

**Wear Behaviour:** Fig.2, shows the variation of the steady state value of the wear rate in the case of Al-2Cu, Al-3Cu, Al-4Cu, Al-5Cu, Al-6Cu specimens as a function of applied load. The wear rate of the alloy is found to be high at 6% copper for both 10N and 30N load and is minimum at 3%Cu for a 10N load and for 30N load it is at 5% copper. Wear rate is found to be fluctuating with different percentages of copper. This fluctuation is may be due to improper manufacturing of alloy during sand casting.

**Figure.2. Wear Rate of Copper**

**Microstructures of worn surfaces:** Fig.3(a), 4(a), 5(a), 6(a) and 7(a) shows the microscopic surfaces of Al-2Cu, Al-3Cu, Al-4Cu, Al-5Cu, Al-6Cu specimens before wear and Fig.3(b), 4(b), 5(b), 6(b) and 7(b) shows the microscopic surfaces of Al-2Cu, Al-3Cu, Al-4Cu, Al-5Cu, Al-6Cu specimens with more worn out surfaces at 6% composition of Al-Cu alloy.

**Figure.3(a). 2% Copper before wear****Figure.3(b). 2% Copper after wear****Figure.4(a). 3% Copper before wear****Figure.4(b). 3% Copper after wear**




Figure.5(a) 4% Copper before wear




Figure.5(b) 4% Copper after wear




Figure.6(a) 5% Copper before wear




Figure.6(b) 5% Copper after wear




Figure.7(a) 6% Copper before wear




Figure.7(b) 6% Copper after wear

#### 4. CONCLUSION

- The Al-Cu alloy was prepared by sand casting using pure form of Aluminium and fine powder of copper.
- The amount of copper was increased from 2-6% of copper.
- Wear rate of Al-Cu alloy is increasing with the increase in percentage of copper.

#### REFERENCES

- Daihong Xiao, Wang J.N, Dongyan Ding S.P, Chen Central South University, Dongyan Ding, Effect of Cu content on the mechanical properties of an Al-Cu-Mg-Ag alloy, Journal of alloys and compounds, 343, 2002, 77-81.
- Jiang J.Q, Tan R.S, Dry sliding wear of an alumina short fibre reinforced Al-Si alloy against steel, Wear, 195, 1996, 106-111.
- Perrin C, Rainforth W.M, The effect of alumina fibre reinforcement on the wear of an Al-4.3%Cu alloy, Wear, 181, 1995, 312.
- Venkataraman B, Sundararajan G, Correlation between the characteristics of the mechanically mixed layer and wear behaviour of aluminium, Al-7075 alloy and Al-MMCs, Wear, 245, 2000, 22-38.
- Xuxing Zhang, Kun-kun Deng, Li W.J, Liang W, Microstructure and mechanical properties of Mg-Al-Ca alloy influenced by SiCp size, Materials Science and Engineering A, 647, 2015, 15-27.
- Zhiyi Liu, Song Bai, Xuanwei Zhou, Yanxia Gu, On strain-induced dissolution of  $\theta'$  and  $\theta$  particles in Al-Cu binary alloy during equal channel angular pressing, 528, 2011, 2217-2222.